



STYLFIX-TILE ADHESIVE TA1

POLYMER MODIFIED CEMENT BASED TILE ADHESIVE

WALLTRON STYLFIX TILE ADHESIVE TA1 is a single component grey cement based polymer modified general purpose tile adhesive for fixing tiles in Interior/Exterior areas.

Product Features:

- Ease of Application
- Superior Durability
- Quick Curing
- Optimal Setting Time
- Superior Adhesion
- Can be used on new as well as old construction for walls and floors

Types of Tiles:

It is generally used for tiles which has porosity greater than 3%

- Clay Tiles
- Non-vitrified Ceramic tiles

Standard Compliance - As per IS 15477:2019 ; EN 12004 C1T



SURFACE PREPARATION

Surface to be tiled must be clean, free from contamination and in Saturated Surface Dry (SSD) condition.

APPLICATION

- Mix STYLFIX Tile Adhesive TA1 in clean water in the proportion 200 - 250 ml of water per kg of Tile adhesive.
- Stir well to get a lump free mix. For larger quantities use appropriate electric mixer.
- Always add powder to water & not vice versa.
- Allow it to mature for 5 minutes. Mix again for 2 minutes & use.
- Spread Nippon Paint Stylfix on the surface using a trowel (Spread that much tile adhesive which can be tiled in 15 mins) and comb using a notched trowel of appropriate depth.
- Press the tile firmly into position with a slight twisting action to maximize contact area.
- Leave adequate joints between the tiles by using spacers.



APPLICATION AREA

- For fixing tiles on the floor as well as walls Interior/Exterior areas.
- Can be used in new as well as old construction

TECHNICAL DETAILS

Specifications

Physical Appearance

Open Time

Pot Life

Adjustability

Recommended mixing

Conforms Type

Limits

Grey Cementitious Powder

Upto 15 minutes

Upto 60 minutes

5 - 15 minutes

200 - 250 ml of water per kg of Tile adhesive

1T & C1T

Coverage:

0.18 - 0.27 sq.mt/kg for 3mm thickness.

Packaging

20 kg, 30 kg

Shelf Life:

Best before 12 months from date of manufacturing in unopened original packing when stored in dry condition.



STYLFIX-TILE ADHESIVE TA2

POLYMER MODIFIED CEMENT BASED TILE ADHESIVE

WALLTRON STYLFIX TILE ADHESIVE TA2 is a single component grey cement based polymer modified general purpose tile adhesive for fixing tiles in Interior/Exterior areas. It can be used for tile on tile application for walls & floors.

Product Features:

- Ease of Application
- Superior Durability
- Quick Curing
- Optimal Setting Time
- Superior Adhesion
- Can be used on new as well as old construction for walls and floors

Types of Tiles:

It is generally used for tiles which has porosity less than or equal to 3%

- Vitrified tiles
- Heavy Tiles like Marble & Granite

Additional Metal anchoring is recommended for exterior application of Heavy Tiles.

Standard Compliance - As per IS 15477:2019 ;
EN 12004 C1T



20 kg, 30 kg

SURFACE PREPARATION

Surface to be tiled must be clean, free from contamination and in Saturated Surface Dry (SSD) condition.

APPLICATION

- Mix STYLFIX Tile Adhesive TA2 in clean water in the proportion 250 - 300 ml of water per Kg of Tile adhesive.
- Stir well to get a lump free mix. For larger quantities use appropriate electric mixer.
- Always add powder to water & not vice versa.
- Allow it to mature for 5 minutes. Mix again for 2 minutes & use.
- Spread Nippon Paint Stylfix on the surface using a trowel (Spread that much tile adhesive which can be tiled in 15 mins) and comb using a notched trowel of appropriate depth.
- Press the tile firmly into position with a slight twisting action to maximize contact area.
- Leave adequate joints between the tiles by using spacers.



APPLICATION AREA

- For fixing tiles on the floor as well as walls Interior/Exterior areas.
- Can be used in new as well as old construction

TECHNICAL DETAILS

Specifications

Physical Appearance

Open Time

Pot Life

Adjustability

Recommended mixing

Conforms Type

Limits

Grey Cementitious Powder

Upto 15 minutes

60 - 90 minutes

5 - 15 minutes

200 - 300 ml of water per kg of Tile adhesive

2T & C2TE

Coverage:

0.18 - 0.27 sq.mt/kg for 3mm thickness.

Packaging

20 kg, 30 kg

Shelf Life:

Best before 12 months from date of manufacturing in unopened original packing when stored in dry condition.



STYLFIX TILE ADHESIVE - TA3

SINGLE COMPONENT CEMENT BASED POLYMER MODIFIED TILE ADHESIVE

WALLTRON STYLFIX - TILE ADHESIVE TA3 is a single component cement-based polymer modified adhesive to enhance slip resistance and Open time for large format tiles. It is suitable for tiles like ceramic tiles, clay tiles, basalt tiles, vitrified tiles, glass mosaic tiles, porcelain tiles, and all natural stones for both Interior & Exterior Floors & walls like concrete and plaster.

Product Features:

- Ease of Application
- Superior Durability
- Quick Curing
- Optimal Setting Time
- Superior Adhesion can be used in new as well as old construction for walls and floors.
- Available in Grey and White color

Typical Application:

- For fixing tiles on the floor as well as walls Interior/Exterior areas.
- Can be used on new as well as old construction.



TECHNICAL DETAILS

Specifications	Limits
Physical Appearance	Grey/White Cementitious Powder
Open Time	15 - 30 mins
Pot Life	60 - 90 mins
Adjustability	5 - 15 mins
Recommended mixing	250 - 300 ml of water per Kg of Tile adhesive
Pull Off Adhesion Test	≥ 1.5Mpa
Conforms Type	2T & C2TE



Coverage:

2 - 3 sq. Ft / kg for 3mm to 4mm thickness. Thickness can be extended up to 12mm.

Shelf Life:

Best before 12 Months from date of manufacturing in unopened original packing when stored in dry condition.

Packaging:

20 kg

TYPES OF TILES

- Unglazed tiles & clay tiles
- Hard natural stones
- Basalt tiles
- Glazed tiles (vitrified and ceramic tiles)
- Mosaic tiles and In-situ mosaic flooring.

Additional Metal anchoring is recommended for exterior application of Heavy Tiles.
Standard Compliance - As per IS 15477:2019 Type 3T

APPLICATION METHOD

- Mix Walltron Stylfix - Tile Adhesive TA3 in clean water in the proportion 250 - 300 ml of water per Kg of Walltron Stylfix Tile adhesive. Stir well to get a lump free mix. For larger quantities use appropriate electric mixer.
- Always add powder to water & not vice versa.
- Allow it to mature for 5 min. Mix again for 2 mins & use.
- Spread Walltron Stylfix on the surface using a trowel (Spread that much tile adhesive which can be tiled in 15 mins) and comb using a notched trowel of appropriate depth.
- Press the tile firmly into position with a slight twisting action to maximize contact area.
- Leave the surface for 24 hours for drying.



STYLFIX TILE ADHESIVE - TA4

SINGLE COMPONENT CEMENT BASED POLYMER MODIFIED TILE ADHESIVE

WALLTRON STYLFIX - TILE ADHESIVE TA4 is a single component cement-based polymer modified adhesive to enhance slip resistance and Open time for large format tiles. It is suitable for tiles like ceramic tiles, clay tiles, basalt tiles, vitrified tiles, glass mosaic tiles, porcelain tiles, dry wall substrates and all natural stones for both Interior & Exterior Floors & walls like concrete and plaster.

Product Features:

- Ease of Application
- Superior Durability
- Quick Curing
- Extended open time
- Optimal Setting Time
- Superior Adhesion can be used in new as well as old construction for walls and floors.

Typical Application:

- For fixing tiles on the floor as well as walls Interior/Exterior areas.
- Can be used on new as well as old construction.



TECHNICAL DETAILS

Specifications	Limits
Physical Appearance	Grey/White Cementitious Powder
Open Time	15 - 30 mins
Pot Life	60 - 90 mins
Adjustability	5 - 15 mins
Recommended mixing	250 - 300 ml of water per Kg of Tile adhesive
Pull Off Adhesion Test	$\geq 1.5\text{Mpa}$
Conforms Type	3TS1 & C2TES1



Coverage:

2 - 3 sq. Ft / kg for 3mm to 4mm thickness. Thickness can be extended up to 12mm.

Shelf Life:

Best before 12 Months from date of manufacturing in unopened original packing when stored in dry condition.

Packaging:

20 kg

TYPES OF TILES

- Unglazed tiles & clay tiles
- Hard natural stones
- Basalt tiles
- Glazed tiles (vitrified and ceramic tiles)
- Mosaic tiles and In-situ mosaic flooring
- All Natural Stones

Additional Metal anchoring is recommended for exterior application of Heavy Tiles.
Standard Compliance - As per IS 15477:2019 Type 4T

APPLICATION METHOD

- Mix Walltron Stylfix - Tile Adhesive TA3 in clean water in the proportion 250 - 300 ml of water per Kg of Walltron Stylfix Tile adhesive. Stir well to get a lump free mix. For larger quantities use appropriate electric mixer.
- Always add powder to water & not vice versa.
- Allow it to mature for 5 min. Mix again for 2 mins & use.
- Spread Walltron Stylfix on the surface using a trowel (Spread that much tile adhesive which can be tiled in 15 mins) and comb using a notched trowel of appropriate depth.
- Press the tile firmly into position with a slight twisting action to maximize contact area.
- Leave the surface for 24 hours for drying.